

AMENDMENTS TO THE SPECIFICATION

Amend the paragraph at page 9, lines 11-17, as follows:

The first crystallized glass of the present invention preferably consists, as represented by mol% based on the following oxides, essentially of from 30 to 65% of SiO_2 , from 5 to 35% of Al_2O_3 , from 1 to 15% of $\text{TiO}_2+\text{ZrO}_2$, from 0 to 30% of Na_2O , from 5 to 30% of K_2O , from 0 to 15% of Li_2O , from 0 to 15% of MgO , from 0 to 15% of CaO , from 0 to 15% of SrO , from 0 to 15% of BaO , from 0 to 15% of ZnO , from 0 to 15% of B_2O_3 , from 0 to 15% of P_2O_5 and from 0 to 15% of Y_2O_3 .